

# Nylacast Moly

PROPERTY	TEST METHOD	NOTES	METRIC	UNITS	IMPERIAL	UNITS
<b>GENERAL</b>						
Colour				Black		Black
Density	ISO1183:1987	Test Method A	g/cm <sup>3</sup>	1.150	lb/inch <sup>3</sup>	0.042
Moisture Absorption (Equilibrium)	ISO 62:1999	50% RH, 23C	%	-	%	-
Water Absorption (24 Hours)	ISO 62:1999(modified)	Immersion, 23C	%	0.20	%	0.20
Water Absorption (Saturation)	ISO 62:1999	Immersion, 23C	%	-	%	-
<b>MECHANICAL</b>						
Tensile strength	ISO 527-1/2:1993	Sample Type 1B, 50mm min <sup>-1</sup>	MPa	85	psi	12328
E-modulus	ISO 527-1/2:1993	Sample Type 1B, 50mm min <sup>-1</sup>	MPa	4100	psi	594656
Elongation at break	ISO 527-1/2:1993	Sample Type 1B, 50mm min <sup>-1</sup>	%	>20	%	>20
Compressive strength	ISO 604:2002	Sample Type B, 5mm min <sup>-1</sup>	MPa	105	psi	15229
Compressive Modulus	ISO 604:2002	Sample Type A, 1mm min <sup>-1</sup>	MPa	3000	psi	435114
Flexural Strength*	ISO 178:2001	1.5mm min <sup>-1</sup>	MPa	115	psi	16679
Flexural Modulus	ISO 178:2001	1.5mm min <sup>-1</sup>	MPa	3700	psi	536641
Izod Impact Strength	ISO 180:2000	Sample Type A (Notched)	kJ/m <sup>2</sup>	4.50	ft.lb/in <sup>2</sup>	2.14
Charpy Impact Strength	ISO 179-2:1999	Notched	kJ/m <sup>2</sup>	-	ft.lb/in <sup>2</sup>	-
Hardness (Shore D)	ISO 868: 2003			85		85
Coefficient of Friction (Dynamic)		31.4m/min, 1.75MPa		0.25		0.25
Limiting PV			Mpa/m. min	-	psi.ft/ min	-
Wear Rate		31.4m/min, 1.75MPa	mg/km	-		-
K-Factor		31.4m/min, 1.75MPa	mm <sup>3</sup> / Nm	-	in <sup>3</sup> min/ ft.lb.hr	-
<b>THERMAL</b>						
Melting Temperature	-		°C	220	°F	428
Glass Transition Temperature (Tg)	ISO 11359-2:1999		°C	-	°F	-
Heat Deflection Temperature HDT/A	ISO 75	1.80MPa	°C	210	°F	410
Heat Deflection Temperature HDT/B	ISO 75	0.45MPa	°C	220	°F	428
Maximum Intermittent Service Temperature	-		°C	170	°F	338
Maximum Continuous Service Temperature	-	5000hrs	°C	105	°F	221
Minimum Intermittent Service Temperature	-		°C	-100	°F	-148
Minimum Continuous Service Temperature	-		°C	-40	°F	-40
Coefficient of Linear Thermal Expansion (TMA)	ISO 11359-2:1999	23°C - 55°C Mean T = 20°C	°C <sup>-1</sup>	8 x 10 <sup>-5</sup>	°F <sup>-1</sup>	4.44 x 10 <sup>-5</sup>
Thermal Conductivity	ISO 8301:1991		W/m°C	-	BTU in/ ft.hr°F	
Flammability	IEC 60695-11-10:2003-08		-	HB	-	HB
<b>ELECTRICAL</b>						
Dielectric Constant	IEC 60250:1969-01	1 MHz		3.7		3.7
Dielectric Constant (Low Frequency)		100Hz		4		4
Dissipation Factor	IEC 60250:1969-01	100Hz	Hz	-	Hz	-
Dielectric Strength	IEC 60243-1:1998-01		kV/mm	25	kV/in	635
Volume Resistivity	IEC 60093:1980-01		ohm.m	1 x 10 <sup>13</sup>	ohm.m	3.93x10 <sup>14</sup>
Surface Resistivity ROA	IEC 60093:1980-01		ohm	1 x 10 <sup>12</sup>	ohm	1 x 10 <sup>12</sup>
Comparative Tracking Index	IEC 60112:2003-01		CTI	600	CTI	600

## PRODUCT AVAILABILITY

Rod	10mm-500mm DIA
Tube	50mm-1000mm OD
Plate	8mm-100mm THICKNESS
Custom Castings	Bespoke
Cut to size	Available upon request

## NOTES

- All Information contained in this literature correspond with our current knowledge of the products.
- Nylacast assume no liability whatsoever in respect of application, conversion or use made of the aforementioned information or product, or any consequence thereof. The buyer undertakes all liability in respect of the application, conversion or use of the aforementioned information or product. Existing intellectual property rights must be observed and Nylacast reserve the right to make technical alterations.