

Nylacast Oilon

PROPERTY	TEST METHOD	NOTES	METRIC	UNITS	IMPERIAL	UNITS
GENERAL						
Colour				Green		Green
Density	ISO1183:1987	Test Method A	g/cm ³	1.140	lb/inch ³	0.041
Moisture Absorption (Equilibrium)	ISO 62:1999	50% RH, 23C	%	-	%	-
Water Absorption (24 Hours)	ISO 62:1999(modified)	Immersion, 23C	%	-	%	-
Water Absorption (Saturation)	ISO 62:1999	Immersion, 23C	%	-	%	-
MECHANICAL						
Tensile strength	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	MPa	75	psi	10878
E-modulus	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	MPa	4000	psi	580152
Elongation at break	ISO 527-1/2:1993	Sample Type 1B, 50mm min ⁻¹	%	>30	%	>30
Compressive strength	ISO 604:2002	Sample Type B, 5mm min ⁻¹	MPa	95	psi	13779
Compressive Modulus	ISO 604:2002	Sample Type A, 1mm min ⁻¹	MPa	2500	psi	362595
Flexural Strength*	ISO 178:2001	1.5mm min ⁻¹	MPa	100	psi	14504
Flexural Modulus	ISO 178:2001	1.5mm min ⁻¹	MPa	3100	psi	449618
Izod Impact Strength	ISO 180:2000	Sample Type A (Notched)	kJ/m ²	6.00	ft.lb/in ²	2.86
Charpy Impact Strength	ISO 179-2:1999	Notched	kJ/m ²	-	ft.lb/in ²	-
Hardness (Shore D)	ISO 868: 2003			83		83
Coefficient of Friction (Dynamic)		31.4m/min, 1.75MPa		0.15		0.15
Limiting PV			Mpa/m. min	-	psi.ft/ min	-
Wear Rate		31.4m/min, 1.75MPa	mg/km	0.11		-
K-Factor		31.4m/min, 1.75MPa	mm ³ /Nm	1.2 x 10 ⁻⁶	in ³ min/ ft.lb.hr	0.60 x 10 ⁻⁹
THERMAL						
Melting Temperature	-		°C	220	°F	428
Glass Transition Temperature (T _g)	ISO 11359-2:1999		°C	-	°F	-
Heat Deflection Temperature HDT/A	ISO 75	1.80MPa	°C	-	°F	-
Heat Deflection Temperature HDT/B	ISO 75	0.45MPa	°C	-	°F	-
Maximum Intermittent Service Temperature	-		°C	170	°F	338
Maximum Continuous Service Temperature	-	5000hrs	°C	110	°F	230
Minimum Intermittent Service Temperature	-		°C	-100	°F	-148
Minimum Continuous Service Temperature	-		°C	-40	°F	-40
Coefficient of Linear Thermal Expansion (TMA)	ISO 11359-2:1999	23°C - 55°C Mean T = 20°C	°C ⁻¹	8 x 10 ⁻⁵	°F ⁻¹	4.44 x 10 ⁻⁵
Thermal Conductivity	ISO 8301:1991		W/m°C	-	BTU in/ ft.hr°F	
Flammability	IEC 60695-11-10:2003-08		-	HB	-	HB
ELECTRICAL						
Dielectric Constant	IEC 60250:1969-01	1 MHz		3.7		3.7
Dielectric Constant (Low Frequency)		100Hz		4		4
Dissipation Factor	IEC 60250:1969-01	100Hz	Hz	-	Hz	-
Dielectric Strength	IEC 60243-1:1998-01		kV/mm	25	kV/in	635
Volume Resistivity	IEC 60093:1980-01		ohm.m	1x10 ¹³	ohm.m	3.93x10 ¹⁵
Surface Resistivity ROA	IEC 60093:1980-01		ohm	1 x 10 ¹²	ohm	1 x 10 ¹²
Comparative Tracking Index	IEC 60112:2003-01		CTI	600	CTI	600

PRODUCT AVAILABILITY

Rod	10mm-500mm DIA
Tube	50mm-1000mm OD
Plate	8mm-100mm THICKNESS
Custom Castings	Bespoke
Cut to size	Available upon request

NOTES

- All Information contained in this literature correspond with our current knowledge of the products.
- Nylacast assume no liability whatsoever in respect of application, conversion or use made of the aforementioned information or product, or any consequence thereof. The buyer undertakes all liability in respect of the application, conversion or use of the aforementioned information or product. Existing intellectual property rights must be observed and Nylacast reserve the right to make technical alterations.