

## POM C Acetal Copolymer

The Copolymer grade is the ideal combination of strength, stiffness and wears resistance. It absorbs very little moisture, is easily machinable and is genuinely porosity-free making it the preferred grade for food contact and medical applications. The product exhibits an elevated resistance to hydrolysis, strong alkalis and thermal-oxidative degradation when compared to acetal homopolymer.

PROPERTY	TEST METHOD	NOTES	METRIC UNITS		IMPERIAL UNITS	
<b>GENERAL</b>						
Colour				White / Black/Blue		White/Black/Blue
Density	ISO1183:1987	Test Method A	g/cm <sup>3</sup>	1.410	lb/inch <sup>3</sup>	0.051
Moisture Absorption (Equilibrium)	ISO 62:1999	50% RH, 23C	%	0.1	%	0.1
Water Absorption (24 Hours)	ISO 62:1999(Modified)	Immersion, 23C	%	0.20	%	0.20
Water Absorption (Saturation)	ISO 62:1999	Immersion, 23C	%	0.90	%	0.90
<b>MECHANICAL</b>						
Tensile Strength	ISO 527-1/2:1993	Sample Type I B, 50mm min <sup>-1</sup>	MPa	70	psi	10153
E-modulus	ISO 527-1/2:1993	Sample Type I B, 50mm min <sup>-1</sup>	MPa	2700	psi	391603
Elongation at break	ISO 527-1/2:1993	Sample Type I B, 50mm min <sup>-1</sup>	%	>15	%	>15
Compressive Strength	ISO 604:2002	Sample Type I B, 50mm min <sup>-1</sup>	MPa	110	psi	15954
Compressive Modulus	ISO 604:2002	Sample Type A, 1mm min <sup>-1</sup>	MPa	2600	psi	377099
Flexural Strength*	ISO 178:2001	1.5mm min <sup>-1</sup>	MPa	80	psi	11603
Flexural Modulus	ISO 178:2001	1.5mm min <sup>-1</sup>	MPa	2600	psi	377099
Izod Impact Strength	ISO 180:2000	Sample Type A (Notched)	KJ/m <sup>2</sup>	7.20	ft.lb/in <sup>2</sup>	3.43
Charpy Impact Strength	ISO 179-2:1999	Notched	KJ/m <sup>2</sup>	-	ft.lb/in <sup>2</sup>	-
Hardness (Shore D)	ISO 868:2003		-	85	-	85
Coefficient of Friction (Dynamic)		3.14m/min, 1.75MPa	-	0.25	-	0.25
Limiting PV			MPa.m.min	6	psi.ft/min	2712
Wear Rate		3.14m/min, 1.75MPa	mg/km	-	-	-
K-Factor		3.14m/min, 1.75MPa	mm <sup>3</sup> /Nm	-	in <sup>3</sup> .min/ft.lb.hr	-
<b>THERMAL</b>						
Melting Temperature	-		°C	170	°F	491
Glass Transition Temperature (Tg)	ISO 11359-2:1999		°C	-60	°F	158
Heat Deflection Temperature HDT/A	ISO 75	1.80MPa	°C	110	°F	185
Heat Deflection Temperature HDT/B	ISO 75	0.45MPa	°C	160	°F	338
Maximum Intermittent Service Temp	-		°C	140	°F	338
Maximum Continuous Service Temp	-	5000Hours	°C	90	°F	230
Minimum Intermittent Service Temp	-		°C	-	°F	-
Minimum Continuous Service Temp	-		°C	-	°F	-
Coefficient of Linear Thermal Expansion(TMA)	ISO 11359-2:1999	23°C-55°C	°C <sup>-1</sup>	9.2x10 <sup>-5</sup>	°F <sup>-1</sup>	5.11x10 <sup>-5</sup>
Thermal Conductivity	ISO 8301:1991	Mean T=20°C	W/m.°C	0.31	BTU in/ft.hr.°F	0.18
Flammability	IEC 60695-11-10:2003-08		-	HB	-	HB
<b>ELECTRICAL</b>						
Dielectric Constant	IEC 60250:1969-01	1MHz	-	3.8	-	3.8
Dielectric Constant (Low Frequency)		100Hz	-	-	-	-
Dissipation Factor	IEC 60250:1969-01	100Hz	Hz	0.005	Hz	0.005
Dielectric Strength	IEC 60243-1:1998-01-01		kV/mm	16.5	kV/in	419.1
Volume Resistivity	IEC 60093:1980-01		ohm.m	1x10 <sup>13</sup>	ohm.in	3.93x10 <sup>14</sup>
Surface Resistivity ROA	IEC 60093:1980-01		ohm	1x10 <sup>13</sup>	ohm	1x10 <sup>13</sup>
Comparative Tracking Index	IEC 60112:2003-01		CTI	600	CTI	600

### AVAILABILITY



ROD: 5mm – 300mm DIA 

PLATE: 6mm – 100mm THICK 

TUBE: 20mm – 250mm 

All information contained in this literature corresponds with our current knowledge of the products. Nylacast assume no liability whatsoever in respect of application, conversion or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, conversion or use of the aforementioned information or products. Existing intellectual property rights must be observed and Nylacast reserve the right to make technical alterations.

UK  +44 (0) 116 276 8558  +44 (0) 116 274 1954

UK e-mail: [sales@nylacast.com](mailto:sales@nylacast.com) website: [www.nylacast.com](http://www.nylacast.com)

NYLACAST LIMITED 

200 Hastings Road . Leicester . England LE5 0HL  
Tel: + 44 (0) 116 2768558 . Fax:+ 44 (0) 116 2741954  
Email: [sales@nylacast.com](mailto:sales@nylacast.com) . Website:[www.nylacast.com](http://www.nylacast.com)

Nylacast Holdings 200 Hastings Road . Leicester . England LE5 0HL  
Nylacast LLC - USA  770 Maple Street . Lebanon, PA. 17046  
Nylacast SA (PTY)  PO BOX 30445 . Jet Park . Johannesburg . South Africa

Reg No. 5949301  
VAT No. GB 897386939